



TG Steels

3344
PRIME

High Speed Steel with a high wear resistance associated with long term cutting performance

3344 PRIME;

- is a high-speed steel that allows it to obtain a very good cleanliness and a very fine structure, which improves its toughness.
- has a very high wear resistance associated with a high hardness and long term cutting performance.
- shows a good suitability for surface treatments such as gas, ionic or salt bath nitriding, as well as PVD or CVD coatings.

Applications

3344 PRIME can be used for high performance fine cutting tools (*punches and dies*) and cold working tools as piercing tools for demanding applications. 3344 PRIME can be used for demanding cutting tools as drills, milling cutters, broaches, taps, dies, spindles, reamers, thread rolling combs, segments for circular saws, etc and also, reamers, shear blades, cold working cylinders.

3344 PRIME is also used for all kind of parts in contact with highly abrasive materials as porcelain.

Main properties

- Excellent wear resistance
- Excellent long term cutting performances
- High hardness
- High compressive strength
- High hardenability

Chemical composition (*typical*)

C	Mn	Si	P	S	Cr	Mo	V	W
1.20	≤ 0.40	≤ 0.45	≤ 0.030	≤ 0.030	4.15	4.95	2.95	6.35

Designation

Werkstoff Nr	ISO	China GB	JIS Japan	UK	AISI USA	Russia Gost	AFNOR	Other / Special
1.3344	HS 6 5 3 / X120 WMoCrV 06 05 04 03	CW6Mo5Cr4V3	SKH53	BM3 class 2	M 3-2	-	-	-



Structure

The structure of the 3344 PRIME is fine and homogeneous without precipitation or alignments of big carbides. The carbide distribution and the micro cleanliness are controlled and in conformity with the Stahl-Eisen Werkstoff Blatt 1570 / 61 standard.

Hardness at the time of delivery

Annealed for 300 HB max

Physical properties

Temperature	20°C	350°C	700°C
Volumic mass kg/m ³	8070	7930	7725
Young Modulus N/mm ²	217000	198000	175000
Thermal conductivity W/m.K	23.5	22.1	22.1
Coefficient of linear expansion 10 ⁻⁶ /K	11.7	12.5	13.0

Heat treatment

SOFT ANNEALING

Temperature: 820 - 850°C, duration 1h + 1h for 25 mm thickness. slow cooling in the furnace (10 to 20°C/h). The atmosphere in the furnace must be reducing to avoid decarburization of the steel.

STRESS RELIEVING

After machining, it is recommended to perform stress relieving at 600 - 650°C for a minimum of 2 hours, followed by slow cooling in the furnace to 450°C.

AUSTENITIZATION

In order to avoid any risk of cracking it is recommended to preheat in 3 steps.

- **1st preheating step:**
temperature: 500°C time: 30 s/mm of thickness
- **2nd preheating step:**
temperature: 850°C time: 30 s/mm of thickness
- **3rd preheating step:**
temperature: 1050°C time: 30 s/mm of thickness

Recommended austenitizing temperature: 1190 - 1280°C. The holding time should not be too long to avoid a risk of grain coarsening and a loss of toughness. It is recommended to keep the part at the austenitizing temperature 30 minutes per inch of thickness as soon as the temperature of the surface reach the austenitization temperature.

SUB ZERO TREATMENT

For parts that need to have high dimensional stability and to increase wear resistance without reducing toughness, it is recommended to perform a subzero treatment at a temperature between -70°C and -190°C for 1 hour for 25 mm of thickness of the part.

The temperature range from -70°C up to -120°C (*named cold treatment of steel*) leads to the complete transformation of austenite into martensite and as a consequence to a better stability associated with an improved hardness and a better wear resistance. On the 3344 PRIME such a treatment leads to an increase of 100% of the wear resistance (*wear ratio*).

The temperature range from -135°C down to -190°C (*named cryotreatment of steel*) leads also to the complete transformation of austenite and also the precipitation of ultra fine carbides improving a lot the wear resistance without modification of the toughness and on 3344 PRIME such a treatment leads to an increase of 200% of the wear resistance (*wear ratio*).

This treatment is optional for common applications.

QUENCHING MEDIUM

Oil at 80°C, vacuum (*pressure > 6 bars*), salt bath 500 - 550°C.


To ensure good toughness, treatment with oil or salt bath is preferable.

After quenching the hardness is 63 - 65 HRC.

TEMPERING

To ensure a minimum residual austenite rate as well as greater tool stability, it is essential to perform a double (*triple is better*) tempering. Each tempering is followed by a cooling under 100°C.

Each tempering time must be at least equal to 1h + 1h for 25 mm of thickness of the treated part (*equivalent thermal thickness*).



Surface treatment

PVD, CVD

3344 PRIME is suitable for all kinds of PVD and CVD treatment as soon as the treatment temperature is 30°C lower than the last tempering temperature.

Polishing

3344 PRIME could be polished the treated state and can be used for applications requiring a sufficiently polish level for translucent parts.

Optimal polishing is achieved by performing consecutive steps of fairly close roughness and stopping each step as soon as the last scratch of the previous step disappears.

Machining

The machining parameters below are given for information only and must be adapted according to the equipment and usual machining conditions.

GRINDING IN ANNEALED CONDITIONS

	Carbide insert		Solid tool
	Rough machining	½ finishing	Finishing
Cutting speed m/min	110 - 130	125 - 160	40 - 50
Feed mm/r	0.35	0.15	0.01 - 0.1
Depth of cut mm	2 - 3	1 - 1.5	0.01 - 0.1

TURNING IN ANNEALED CONDITIONS

	Carbide tool		HSS tool
	Rough turning	Finishing	Turning
Cutting speed m/min	110 - 140	165 - 200	15
Feed mm/r	0.35	0.15	0.1 - 0.2
Depth of cut mm	2 - 3	1 - 1.5	0.5 - 2.0

DRILLING IN ANNEALED CONDITIONS: HSS TWIST DRILL

Drill diameter mm	Cutting speed m/min	Feed mm/r
<5	11	0.07
5-10		0.15
10-15		0.22
15-20		0.30

DRILLING IN ANNEALED CONDITIONS: CARBIDE DRILL

	Insert	Solid
Cutting speed m/min	130	70
Feed mm / r	0.10	0.20

FINE GRINDING

General indications for grinding wheels to be used on 3344 PRIME in the heat treated condition. Usually, rather soft vitrified aluminum oxide grinding wheels (*grades G for plane grinding to K for cylindrical grinding*) are used. Particular attention will be paid to effective cooling of the surface during grinding to prevent degradation of the material surface.

ELECTRO-DISCHARGE MACHINING

3344 PRIME is also suitable for EDM machining (*wire or electrode*). Preferably, the machining will be carried out with a low current density and a high frequency in order to limit the thickness of the white layer as much as possible.

Then it is necessary to carry out a stress relieving at 25°C below the last tempering in order to reduce the level of residual stresses (*which could lead to a risk of cracking*) and to carry out a polishing to completely remove the white layer formed during the discharge machining process.

Welding

3344 PRIME cannot be welded.



TG Steels

E info@tgsteels.com W www.tgsteels.com

Atlas Special Steels, s.l.
Avinguda de Can Sucarrats, 88-92,
08191 Rubí, Barcelona, Spain
+34 938 233 590
info@atlassteels.eu

Atlas Special Steels Unipessoal, Lda
Rua do Antuã, nr. 64 pavilhão A e B
3720-558 Travanca – OAZ, Portugal
+351 256 245 497
info@atlassteels.eu

Five Star Special Steel Europe srl
Via Glenn Curtiss, 9, 25018
Montichiari BS, Italy
+39 030 524 3724
info@fssseurope.com

GNG Consultoria
Rua Ituporanga, 210 – Bom Retiro
Joinville – SC – 89222-430
+55 47 99669-5557
marcus@gngconsultoria.com.br

OSS Canada Special Steel Inc
2384 Speers Rd, Oakville,
ON, Canada L6L 5M2
905-827-5888
sales@oss-material.ca

OSS Special Steel Inc.
2015 Mitchell Blvd Suite C
Schaumburg, IL 60193
(618) 426 – 6158
sales@oss-material.com

TG Steels s.r.o.
Libušina 850, Dubí 272 03
Kladno, Czech Republic
info@tgsteels.com

TG Middle East
Kocaeli KOBİ OSB, Köşeler Mh.,
3. Cd., No: 15 Dilovası, Kocaeli, Türkiye
+90 262 728 11 67 (pbx)
info@tgme.com.tr