




Canada  
SPECIAL STEEL INC



# Alloy 400

SHEET AND PLATE



## Applications

### INDUSTRIAL

Power Plants, Chemical Industry, Mineral Oil  
Distillation Plants, Offshore Platforms.

## Features

- Resistance against chloride-induced stress corrosion
- Excellent strength even at low application temperatures
- Easy processing compared to other high-alloy materials

## Standard

ASTM B127

## Material

Alloy 400 / UNS N04400 / 2.4360&2.4361

## Surface

Bright annealed / annealed

## Package

Wooden case

## Chemical composition (Nominal) %

Grade	Ni	Cu	Fe	Mn	C	Si	S
Alloy 400	63.0 min	28.0-34.0 max	2.5 max	2.0 max	0.3 max	0.5 max	0.024 max

## Physical properties

Density 8.82 g/cm<sup>3</sup> (0.32 lb/in<sup>3</sup>) at 20°C

## Mechanical properties

Heat Treatment	Tensile Strength, min, psi (MPa)	Yield Strength, min. (0.2% offset), min, psi (MPa)	Elongation in 2 in. or 50 mm (or 4 D), min, %
Hot-Rolled Plate: Annealed	70 000 (485)	28 000 (195)	35
Hot-Rolled Plate: As-rolled	75 000 (515)	40 000 (275)	25
Hot-Rolled Sheet: Annealed	70 000 (485)	28 000 (195)	35
Cold-Rolled Sheet: Annealed	70 000 to 85 000 (485 to 585)	28 000 (195)	35

## Heat treatment

### Annealed

The soft annealing should be performed at temperatures of 700 to 900°C (1,292 to 1,652°F), preferably at about 825°C (1,517°F).

### Stress-Relieved

Stress-relief annealing at about 550 to 650°C (1,022 to 1,202°F) should then occur, in order to prevent stress corrosion cracking.